

Toufic T. Berbari & Fils

QUARTIER CHRIST ROI
ZOUK MOSBEH
LIBAN

TEL : 09 218271 - 09 218272
FAX : +961 9 218272
B.P. : 250 ZOUK MICKAEL
E- MAIL: info@noula.com.lb

DATA SHEET FOR UNDERCOAT ALKYD PAINT

The use of high quality long oil alkyd resin make **NOULA** undercoat ideal where high performance are needed, and yellowing effect reduced.

NOULA undercoat is ideal on radiators and hot surfaces up to 80oc.

WHERE A PRIMING COAT IS NEEDED —

A Priming Coat must be applied on New Surfaces — such as New Plaster, New Burlap, New Canvas, New Wood and New Metal; also on Walls from which Wall Paper and Kalsomine have been removed; also newly .plastered cracks; also, over old Casein Paint and Flat Wall Paint because they are porous.

PREPARING OLD PAINTED WALLS

Scales and peels should be removed. Wipe off cobwebs, soot and loose dirt with soft, lint less cloth. For best results wash with warm water to which ammonia has been added. Wipe dry. Let dry thoroughly before applying pigmented **NOULA** undercoat.

PAINTING WOODWORK —

On previously painted surfaces, clean and sand thoroughly to remove dirt, polish, wax, etc. and to lower the gloss. Prime with pigmented **NOULA** undercoat. in smooth, even strokes. On new wood surfaces, apply directly **NOULA** undercoat.

TECHNICAL DATA

UNDERCOAT

-Resistance to chalking (ASTM D659)	No 8
-Pfund hiding power	800 microns
-Impression hardness (500gr, l)	1.5 mm
-Hegmann fineness of grind	0.2 mil
-Impact resistance	80 in-pounds
-Abrasion resistance (ASTM D968)	6.2 l/mil

NOULA undercoat paint must be thinned only with white spirit.
One U.S. gallon covers 50sqm per coat.

Disclaimer

It is the user responsibility to get sure of the use of the product in a correct way and place.
As Noura paints has no control over the improper usage of the product we cannot be hold responsible for any consequences associated with their use.