

Toufic T. Berbari & Fils

QUARTIER CHRIST ROI
ZOUK MOSBEH
LIBAN

TEL : 09 218271 - 09 218272
FAX : +961 9 218272
B.P. : 250 ZOUK MICKAEL
E- MAIL: info@noula.com.lb

NOULA EPOXY: a 2K solvent base Epoxy/Amine-system.

NOULA EPOXY is ideal where high performances are needed, such as:

- Resistance against chemicals (gas stations, chemical plants)
- Improved mechanical properties for traffic with forklifts and trucks (warehouses, park decks)

METAL SURFACES must be primed with **NOULA EPOXY** zinc phosphate metal primer.

For better results:

- Room and substrate temperature must be $> 8^{\circ}\text{C}$
- Relative humidity $< 80\%$
- Good air circulation is needed.

Technical features:

- Mix ratio epoxy/hardener 4/1byv.
- Term of use ~ 2.30 h
- Dust free ~ 3-4 h
- Tack free (recoverable) ~ 12 h -Complete hardening after 7days

Surface to cover must be solid and clean. Mechanical roughening is better than chemical treatment. If chemically treated, surface must be very well cleaned.

Disclaimer

It is the user responsibility to get sure of the use of the product in a correct way and place.

As Noula paints has no control over the improper usage of the product we cannot be hold responsible for any consequences associated with their use.

للحصول على شروط السماكة المطلوبة. يجب اعتبار المعطيات التالية.

العبوة سعة خمسة كيلوات و نصف كافية لتغطية مساحة 25 متر مربع بسماكة 170 مبكرون رطب ما يساوي 125 مبكرون بعد النشاف للوجه الواحد.

من أجل الحصول على أعلى و أجود نوعية ، يتم اختيار المواد الأولية بتقني و تحفظ.

راتنجات الأيبوكسي و مادة النشاف من شركة **CIBA** العالمية.

ثاني أوكسيد التيتانيوم من شركة **KERR McGee** ألمانية .

فوسفات الزنك من شركة **WAARDALS** النرويجية .