

# *Toufic T. Berbari & Fils*

QUARTIER CHRIST ROI  
ZOUK MOSBEH  
LIBAN  
-----

TEL : 09 218271 - 09 218272  
FAX : +961 9 218272  
B.P. : 250 ZOUK MICKAEL  
E- MAIL: info@noula.com.lb

## **DATA SHEET FOR SUPER ENAMEL ALKYD PAINT**

The use of high-quality long oil alkyd resin makes **NOULA** super enamel ideal where high performance are needed.

**NOULA** super enamel is ideal where very smooth and glossy surfaces are required.

### **WHERE A PRIMING COAT IS NEEDED —**

A Priming Coat must be applied before this finish is put on New Surfaces — such as New Plaster, New Burlap, New Canvas, New Wood and New Metal; also on Walls from which Wall Paper and Kalsomine have been removed; also newly .plastered cracks; also, over old Casein Paint and Flat Wall Paint because they are porous. But over an enameled, gloss, semi-gloss or other sealed surface, this finish may be applied with out a priming coat.

### **PRIMING COAT —**

On unpainted plaster, wood, metal or other new surfaces or on old surfaces from which paint, varnish, kalsomine or wall paper has been completely removed, use our pigmented sealer, undercoat or metal primer.

### **PREPARING OLD PAINTED WALLS**

Scales and peels should be removed. Wipe off cobwebs, soot and loose dirt with soft, lint less cloth. For best results wash with warm water to which ammonia has been added. Wipe dry. Let dry thoroughly. Prime bare spots before painting.

### **PAINTING WOODWORK —**

On previously painted surfaces, clean and sand thoroughly to remove dirt, polish, wax, etc. and to lower the gloss. Apply this material in smooth, even strokes. On new wood, a priming coat must be applied.

# *Toufic T. Berbari & Fils*

QUARTIER CHRIST ROI  
ZOUK MOSBEH  
LIBAN  
-----

TEL : 09 218271 - 09 218272  
FAX : +961 9 218272  
B.P. : 250 ZOUK MICKAEL  
E- MAIL: info@noula.com.lb

## **TECHNICAL DATA**

## **SUPER ENAMEL**

-Resistance to chalking (ASTM D659)	No 8
-Pfund hiding power	130 microns
-Impression hardness (500gr, l)	1.7 mm
-Hegmann fineness of grind	0.1 mil
-Impact resistance	82 in-pounds
-Abrasion resistance (ASTM D968)	6.9 l/mil

**NOULA** super enamel paint must be thinned only with white spirit.  
One U.S. gallon covers 50sqm per coat.

## **Disclaimer**

It is the user responsibility to get sure of the use of the product in a correct way and place.  
As Noula paints has no control over the improper usage of the product we cannot be hold responsible for any consequences associated with their use.