# Toufic T. Berbari & Fils

QUARTIER CHRIST ROI ZOUK MOSBEH LIBAN

--- --- ---

TEL: 09 218271 - 09 218272

FAX: +961 9 218272 B.P.: 250 ZOUK MICKAEL E- MAIL: info@noula.com.lb

## DATA SHEET FOR SEMI-GLOSS ALKYD PAINT

The use of high quality medium oil alkyd resin make **NOULA** semi-gloss ideal where high performance are needed, and yellowing effect reduced.

**NOULA** semi-gloss is ideal on radiators and hot surfaces up to 90oc.

#### WHERE A PRIMING COAT IS NEEDED —

A Priming Coat must be applied before this finish is put on New Surfaces — such as New Plaster, New Burlap, New Canvas, New Wood and New Metal; also on Walls from which Wall Paper and Kalsomine have been removed; also newly .plastered cracks; also, over old Casein Paint and Flat Wall Paint because they are porous. But over an enameled, gloss, semi-gloss or other sealed surface, this finish may be applied with out a priming coat.

#### PRIMING COAT —

On unpainted plaster, wood, metal or other new surfaces or on old surfaces from which paint, varnish, kalsomine or wall paper has been completely removed, use our pigmented sealer or undercoat.

### PREPARING OLD PAINTED WALLS

Scales and peels should be removed. Wipe off cobwebs, soot and loose dirt with soft, lint less cloth. For best results wash with warm water to which ammonia has been added. Wipe dry. Let dry thoroughly. Prime bare spots before painting.

### PAINTING WOODWORK —

On previously painted surfaces, clean and sand thoroughly to remove dirt, polish, wax, etc. and to lower the gloss. Apply this material in smooth, even strokes. On new wood, a priming coat must be applied.

# Toufic T. Berbari & Fils

QUARTIER CHRIST ROI ZOUK MOSBEH LIBAN FAX: +961 9 218272 B.P.: 250 ZOUK MICKAEL

B.P.: 250 ZOUK MICKAEL E-MAIL: info@noula.com.lb

TEL: 09 218271 - 09 218272

### **TECHNICAL DATA**

## **SEMI-GLOSS**

-Resistance to chalking (ASTM D659) No 8

-Pfund hiding power 130 microns

-Impression hardness (500gr, 1) 1.7 mm

-Hegmann fineness of grind 0.1 mil

-Impact resistance 82 in-pounds

-Abrasion resistance (ASTM D968) 6.9 l/mil

**NOULA** semi-gloss paint must be thinned only with white spirit. One U.S. gallon covers 50sqm per coat.

#### **Disclaimer**

It is the user responsibility to get sure of the use of the product in a correct way and place. As Noula paints has no control over the improper usage of the product we cannot be hold responsible for any consequences associated with their use.